VISUALS PROPERTIES -

Type & Name	Properties	Common use	Burning
POLYETHYLENE TEREPHTHALATE	Clear, Tough, Solvent Resistant, Barrier To Gas And Moisture, Softens At 80°	Soft Drink, Water Bottles, Salad Domes, Bisquit Trays, Food Containers.	Yellow Flame Little Smoke
2 HDPE HIGH-DENSITY POLYETHYLENE	Hard To Semi-Flexible, Resistant To Chemicals And Moisture, Waxy Surface, Softens At 75°	Shopping Bags, Freezer Bags, Milk Bottles, Juice Bottles, Iceacream Containers, Shampoo, Crates.	Difficult To ignite smells like candle
23) PV(POLYVINYL CHLORIDE	Strong, Tough, Can Be Clear And Solvent, Softens At 60°	Cosmetic Containers, Electrical Condult, Plumbing Pipes, Blister Packs, Roof Sheeting, Garden Hose.	Yellow Flame Green Spurts
221DPE LOW-DENSITY POLYETHYLENE	Soft, Flexible, Waxy Surface, Scratches Easily, Softens At 70°	Cling Wrap, Garbage Bags, Squeeze Bottles, Refuse Bags, Mulch Film.	Difficult To Ignite Smells Like Candle
25 PP POLYPROPYLENE	Hard But Still Flexible, Waxy Surface, Translucent, Withstands Solvents, Softens At 140°	Bottles, Icecream Tubes, Straws, Flower- Pots, Dishes, Garden Furniture, Food Containers.	Blue Yellow Tipped Flame
263PS POLYSTYRENE	Clear, Glassy, Opaque, Semi Tough, Softens At 95°	CD Cases, Plastic Cutlery, Imitation Glass, Foamed Meat Trays, Brittle Toys.	Dense Smoke
20THER ALL OTHER PLASTICS	Properties Depend On The Type Of Plastic	Automotive, Electronics, Packaging	All Other Plastics

